

IN THE CLAIMS:

1. (Currently Amended) An organic electroluminescent device comprising:
at least two or more emitting layers between an anode and a cathode, and
an intermediate electrode layer being interposed between emitting layers,
the intermediate electrode layer being a single layer or a multilayer structure, at least one
of the layers comprising a semiconductive material and at least one of the layers comprising a
donor that is an alkali metal and/or an alkaline earth metal,

the semiconductive material comprising an acceptor that is at least one conductive oxide
comprising a transition metal selected from the group consisting of NbO_x, LaO_x, NdO_x, SmO_x,
EuO_x, MoO_x, WO_x, OsO_x, IrO_x and PtO_x, wherein x is 0.2 to 5;

wherein the acceptor is the main constituent of the intermediate electrode layer and the
ratio of donor to acceptor in the intermediate electrode layer is between 2:98 to 20:80.

2. – 27. (Cancelled)

28. (Previously Presented) A display comprising a screen comprising the organic
electroluminescent device according to claim 1.

29. – 32. (Cancelled)

33. (Previously Presented) The organic electroluminescent device according to claim 1,
wherein the conductive oxide is MoO_x.

34. (Currently Amended) The organic electroluminescent device according to claim [[38]] 1, wherein the conductive oxide is MoO_x , x is 2 to 3, and the donor is Cs.

35. – 38. (Cancelled)

39. (Previously Presented) The organic electroluminescent device according to claim 1, further comprising an electron injecting layer on the anode side of the intermediate layer, wherein the electron injecting layer comprises an alkali metal compound or a reducing dopant.

40. (Previously Presented) The organic electroluminescent device according to claim 1, wherein the intermediate electrode layer has a resistivity between 0.001 and 10,000 $\Omega\cdot\text{cm}$.

41. (New) The organic electroluminescent device according to claim 1, wherein the intermediate electrode layer has a resistivity between 0.01 and 100 $\Omega\cdot\text{cm}$.

42. (New) An organic electroluminescent device comprising:
at least two or more emitting layers between an anode and a cathode, and
an intermediate electrode layer being interposed between emitting layers,
the intermediate electrode layer being a single layer or a multilayer structure, at least one of the layers comprising a semiconductive material and at least one of the layers comprising a donor that is an alkali metal and/or an alkaline earth metal, and
the semiconductive material comprising MoO_x , wherein x is 0.2 to 5.